crevi

5 years guarantee • sanitized (antimicrobial)

General Information



Composition 76%PP17%PES REC 4%OF 3%CO REC

Width 140 + 4cm

Weight

 $568 \, \text{gr/m2} \pm 5 \, \%$ $795 \,\mathrm{gr/lm} \pm 5\,\%$

Custom code UE: 5407.83.00 USA: 5407.83.00.90

Laboratory test number IN-00807-2018-B 2020AN1320 EN ISO 20743

Specifications

Seam slippage resistance (mm)

Warp: 1,90 Weft: 1,70

EN ISO 13936/2:2004

Abrasion resistance (End point)

35.000 EN ISO 12947-2:1998

Abrasion resistance (change of aspect: 3000 cycles)

3-4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)

Pilling resistance

4-5 EN ISO 12945/2:2000

Lightfastness

>6 EN ISO 105-B02:1998

Colour fastness to rubbing

Dry: <u>4-5</u> Wet: 4-5

EN ISO 105-X12:2002

Care

PERFORMANCE+

Easy to clean, longlasting fabrics

Washing conditions









Soiling and cleanability

4-5 FORD FLTM BN 112-08:2005

Dimensional change domestic washing and drying (%)

Warp: <u>-3</u> Weft: -1

When confectioning or washing the sofa cover with velcro please attach a protective cloth.

Antibacterial activity Strong antibacterial property

>3 EN ISO 20743:2013




Ignitability

BS5852 Source O EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013

BS5852 Source 1 EN1021-Part 2:2006 UNI 9175 Clase 3IM

Environmental considerations



17% GRS recycled PET bottles 4% Circular yarn from own waste 3% Recycled CO

76% Low impact yarn (PP)

Life cycle analysis

Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint

3,6 kg CO₂ eq/m 12,62% less since 2020

Water consumption

69,9 liters/m 25,24% less since 2020



UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH

Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology: Life Cycle Analysis. ISO 14040 standard.

Own data, Ecoinvent 3.6 database and published data.

1 linear meters, 140 cm width.

Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03

Designed and Crafted in Terrassa (Barcelona)

Certificates















