

5 years guarantee

General Information



Composition

54%PES REC 26%PP 20%PES

Width

140 + 4cm

Weight

450 gr/m² ± 5 %
630 gr/lm ± 5 %

Custom code

UE: 5801.36.00
USA: 5801.36.00.20

Laboratory test number

IN-00680/2017-B-1 87019
IN-01415-2'15 2024RA1613

Specifications

Seam slippage resistance (mm)

Warp: 3.80
Weft: 3.90
EN ISO 13936/2:2004

Abrasion resistance (End point)

50.000 EN ISO 12947-2:2016

Abrasion resistance

(change of aspect: 3000 cycles)
4-5 EN ISO 12947/4:1998
and EN 14465:2003 (Annex A)

Pilling resistance

4-5 EN ISO 12945/2:2000

Lightfastness

6-7 EN ISO 105-B02:1998
and 105 B02/A01:2002

Colour fastness to rubbing

Dry: 4-5
Wet: 4-5
EN ISO 105-X12:2002

Colour fastness to domestic and commercial laundering (30°)

4-5 EN ISO 105-C06:1997/AC:2009

Care

PERFORMANCE+

Easy to clean, longlasting fabrics

Washing conditions



Soiling and cleanability

4 FORD FLTM BN 112-08:2005

Dimensional change domestic washing and drying (%)

Warp: -2
Weft: -1.5
EN ISO 3759:2008, EN ISO 6330:2000
and EN ISO 5077:2008


When confectioning or washing the sofa cover with velcro please attach a protective cloth.

Ignitability

BS5852 Source 0
EN1021-Part 1:2006
CAL TB 117:2013
NFPA 260:2013

Upon Request:
BS5852 Source 1
EN1021-Part 2:2006
BS 7176 Low Hazard
UNI 9175 Clase 3IM

Environmental considerations



54% GRS recycled PET bottles
26% Low impact yarn (PP)
20% PES

Life cycle analysis

Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint

4,06 kg CO₂ eq / m
6,67% less since 2020

Water consumption

105,04 liters / m
3,48% less since 2020



UNIVERSITAT POLITÈCNICA DE CATALUNYA
BARCELONATECH

Escola Superior d'Enginyeries Industrial,
Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology:
Life Cycle Analysis. ISO 14040 standard.

Functional unit:
1 linear meters, 140 cm width.

Database:
Own data, Ecoinvent 3.6 database and published data.

Calculation methodology:
Aware V1.02
ReCiPe Midpoint (H) 2016 v1.04
ReCiPe Endpoint (H) 2016 v1.04
IPCC 2013 GWP 100a v1.03
Software: SimaPro 9.4.0.1

Designed and Crafted
in Terrassa (Barcelona)

