


5 years guarantee

General Information	Specifications	Care
 Composition 77%PP 23%PES REC Width 140 + 4cm Weight 586 gr/m2 ± 5 % 820 gr/lm ± 5 % Custom code UE: 5407.73.00 USA: 5407.73.20.60 Laboratory test number 4858-004T_1_EN 4858-003T_1A_EN	Seam slippage resistance (mm) Warp: 2,10 Weft: 1,20 EN ISO 13936/2:2004 Abrasion resistance (End point) 26.667 EN ISO 12947-2:2016 Pilling resistance 4 EN ISO 12945/2:2000 Lightfastness >6 EN ISO 105-B02:1998 and 105 B02/A01:2002 Colour fastness to rubbing Dry: 4-5 Wet: 4-5 EN ISO 105-X12:2002	PERFORMANCE+ Easy to clean, longlasting fabrics Washing conditions  Soiling and cleanability 4-5 FORD FLTM BN 112-08:2005 When confectioning or washing the sofa cover with velcro please attach a protective cloth.
		Ignitability BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013 Upon Request: BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM

Environmental considerations

 23% recycled yarn 23% GRS recycled PET bottles 77% Low impact yarn (PP)	Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling. Carbon footprint 3,83 kg CO₂ eq / m Water consumption 78,69 liters / m	UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa Study realized in collaboration with UPC Methodology: Life Cycle Analysis. ISO 14040 standard. Functional unit: 1 linear meters, 140 cm width. Database: Own data, Ecoinvent 3.6 database and published data. Calculation methodology: Aware V1.02 ReCiPe Midpoint (H) 2016 v1.04 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03 Software: SimaPro 9.4.0.1
--	---	---

Designed and Crafted
in Terrassa (Barcelona)

