Gres

crevin

5 years guarantee • easy to clean • durability

General Information



Composition
49%PES REC 21%PP REC 17%PES
7%CO REC 6%OF REC

Width
140 + 4cm

Weight
496 gr/m2 ± 5 %
695 gr/lm ± 5 %

Custom code
UE: 5801.36.00
USA: 5801.36.00.20

Laboratory test number
IN-01082-2024-1 / 2024RA1614

Specifications

Seam slippage resistance (mm)
Warp: 2,2
Weft: 1,9
EN ISO 13936/2:2004

Abrasion resistance (End point)
50.000 EN ISO 12947-2:2016


Pilling resistance
4-5 EN ISO 12945/2:2000

Lightfastness
5-6 EN ISO 105-B02:1998
and 105 B02/A01:2002

Care

PERFORMANCE+
Easy to clean, longlasting fabrics

Washing conditions



Soiling and cleanability
4 FORD FLTM BN 112-08:2005

Dimensional change domestic washing and drying (%)
Warp: -2
Weft: -2
EN ISO 3759:2008, EN ISO 6330:2000
and EN ISO 5077:2008


When confectioning or washing the sofa cover with velcro please attach a protective cloth.

Ignitability

BS5852 Source 0
EN1021-Part 1:2006
CAL TB 117:2013
NFPA 260:2013

Upon Request:
BS5852 Source 1
EN1021-Part 2:2006
BS 7176 Low Hazard
UNI 9175 Clase 3IM

Environmental considerations



49% GRS recycled PET bottles
21% Recycled PP
7% Recycled CO
6% Circular yarn from own waste
17% PES

Life cycle analysis
Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint

4,45 kg CO_2 eq/m
-

Water consumption

100,12 liters/m
-

UNIVERSITAT POLITÈCNICA DE CATALUNYA
BARCELONATECH
Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology:
Life Cycle Analysis. ISO 14040 standard.

Functional unit:
1 linear meters, 140 cm width.

Database:
Own data, Ecoinvent 3.6 database and published data.

Calculation methodology:
Aware V1.02
ReCiPe Midpoint (H) 2016 v1.04
ReCiPe Endpoint (H) 2016 v1.04
IPCC 2013 GWP 100a v1.03
Software: SimaPro 9.4.0.1

Designed and Crafted in Terrassa (Barcelona)

Rev. nº: 3 - 15/04/2024 *Results that are underlined have been obtained by Crevin's internal laboratory and must therefore be seen as indicative.