

fire resistant • easy to clean • durability

General Information	Specifications	Care
 Composition 35%PES REC 32%PES 18%MA 15%CO REC Width 140 + 4cm Weight 525 gr/m2 ± 5 % 735 gr/lm ± 5 % Custom code UE: 5801.36.00 USA: 5801.36.00.20 Laboratory test number IN-01060-2024-1	Seam slippage resistance (mm) Warp: 1,7 Weft: 1,5 EN ISO 13936/2:2004 Abrasion resistance (Fully worn off) 70.000 EN ISO 12947-2:2016 Pilling resistance 4-5 EN ISO 12945/2:2000 Lightfastness 5-6 EN ISO 105-B02:1998 and 105 B02/A01:2002	PERFORMANCE+ Easy to clean, longlasting fabrics Washing conditions  Soiling and cleanability 4-5 FORD FLTM BN 112-08:2005 Dimensional change domestic washing and drying (%) Warp: -3% Weft: -3% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008 When confectioning or washing the sofa cover with velcro please attach a protective cloth.
		Ignitability BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013 BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM
Environmental considerations		
 35% GRS recycled PET bottles 15% Recycled CO 32% PES 18% MA	Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling. Carbon footprint 4,57 kg CO₂ eq /m Water consumption 161 liters/m	 UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa Study realized in collaboration with UPC Methodology: Life Cycle Analysis. ISO 14040 standard. Functional unit: 1 linear meters, 140 cm width. Database: Own data, Ecoinvent 3.6 database and published data. Calculation methodology: Aware V1.02 ReCiPe Midpoint (H) 2016 v1.04 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03 Software: SimaPro 9.4.0.1
Designed and Crafted in Terrassa (Barcelona)		