

easy stain release

General Information



Composition
75%PES 25%PES REC

Width
140 + 4cm

Weight
521 gr/m2 ± 5 %
730 gr/lm ± 5 %

Custom code
UE: 5801.36.00
USA: 5801.36.00.20

Laboratory test number
IN-00933-2023-1
2024AN0234

Specifications

Seam slippage resistance (mm)
Warp: 5,4
Weft: 2,4
EN ISO 13936/2:2004

Abrasion resistance (End point)
60.000 EN ISO 12947-2:2016

Abrasion resistance
(change of aspect: 3000 cycles)
4-5 EN ISO 12947/4:1998
and EN 14465:2003 (Annex A)

Pilling resistance
4-5 EN ISO 12945/2:2000

Lightfastness
5-6 EN ISO 105-B02:1998
and 105 B02/A01:2002

Colour fastness to rubbing
Dry: 4-5
Wet: 4-5
EN ISO 105-X12:2002

Care

Washing conditions

Soiling and cleanability
4 FORD FLTm BN 112-08:2005


Dimensional change domestic washing and drying (%)
Warp: -2%
Weft: -1%
EN ISO 3759:2008, EN ISO 6330:2000
and EN ISO 5077:2008

Iron on reverse side.
When confectioning or washing the sofa cover with veloro please attach a protective cloth.

Ignitability

BS5852 Source 0
EN1021-Part 1:2006
CAL TB 117:2013
NFPA 260:2013

Environmental considerations



25% GRS recycled PET bottles
75% PES

Life cycle analysis
Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint
4,55 kg CO₂ eq / m
9% less since 2023

Water consumption
88,85 liters / m
6,96% less since 2023

UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH
Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa
Study realized in collaboration with UPC

Methodology:
Life Cycle Analysis. ISO 14040 standard.

Functional unit:
1 linear meters, 140 cm width.

Database:
Own data, Ecoinvent 3.6 database and published data.

Calculation methodology:
Aware V1.02
ReCiPe Midpoint (H) 2016 v1.04
ReCiPe Endpoint (H) 2016 v1.04
IPCC 2013 GWP 100a v1.03
Software: SimaPro 9.4.0.1

Designed and Crafted
in Terrassa (Barcelona)

