Pícar-Fr

crevin

fire resistant • easy to clean • durability

General Information



Composition
44%PET REC 35%PP 11%MA 6%CO REC 4%PES

Width
140 + 4cm

Weight
668 gr/m2 ± 5 %
935 gr/lm ± 5 %

Custom code
UE: 5801.36.00
USA: 5801.36.00.20

Laboratory test number
IN-00662-2025-1

Specifications

Seam slippage resistance (mm)
Warp: 1,7
Weft: 1,7
EN ISO 13936/2:2004

Abrasion resistance (End point)
60.000 EN ISO 12947-2:2016

Abrasion resistance (change of aspect: 3000 cycles)
4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)

Pilling resistance
5 EN ISO 12945/2:2000

Lightfastness
>6 EN ISO 105-B02:1998 and 105 B02/A01:2002

Colour fastness to rubbing
Dry: 4-5
Wet: 4-5
EN ISO 105-X12:2002

Care

PERFORMANCE+
Easy to clean, longlasting fabrics

Washing conditions



Soiling and cleanability
4 FORD FLTM BN 112-08:2005

Dimensional change domestic washing and drying at 30º (%)
Warp: -3%
Weft: -3%
EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008


***Dimensional change domestic washing and drying at 40º (%)**
Warp: -4%
Weft: -4%
EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008

When confectioning or washing the sofa cover with velcro please attach a protective cloth.

Ignitability

BS5852 Source 0	BS5852 Source 1
EN1021-Part 1:2006	EN1021-Part 2:2006
CAL TB 117:2013	BS 7176 Low Hazard
NFPA 260:2013	UNI 9175 Clase 3IM

Environmental considerations



44% GRS recycled PET bottles
6% Recycled CO
35% Low impact yarn (PP)
11% MA
4% PES

Life cycle analysis
Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint
4,91 kg CO_2 eq/m

Water consumption
133,47 liters/m

UNIVERSITAT POLITÈCNICA DE CATALUNYA
BARCELONATECH
Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology:
Life Cycle Analysis. ISO 14040 standard.

Functional unit:
1 linear meters, 140 cm width.

Database:
Own data, Ecoinvent 3.6 database and published data.

Calculation methodology:
Aware V1.02
ReCiPe Midpoint (H) 2016 v1.04
ReCiPe Endpoint (H) 2016 v1.04
IPCC 2013 GWP 100a v1.03
Software: SimaPro 9.4.0.1

Designed and Crafted in Terrassa (Barcelona)

Rev. nº: 6 - 16/10/2025 *Results that are underlined have been obtained by Crevin's internal laboratory and must therefore be seen as indicative.