Sacco

crevin

5 years guarantee • easy to clean • durability

General Information



Composition
80%PP 15%PES REC 2%CO 3%OF REC

Width
140 + 4cm

Weight
571 gr/m2 ± 5 %
800 gr/lm ± 5 %

Custom code
UE: 5407.73.00
USA: 5407.73.20.60

Laboratory test number
IN-00704/2019-B-1

Specifications

Seam slippage resistance (mm)
Warp: 1,50
Weft: 1,60
EN ISO 13936/2:2004

Abrasion resistance (End point)
80.000 EN ISO 12947-2:2016

Abrasion resistance (change of aspect: 3000 cycles)
4-5 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)

Pilling resistance
4-5 EN ISO 12945/2:2000

Lightfastness
>6 EN ISO 105-B02:1998 and 105 B02/A01:2002

Colour fastness to rubbing
Dry: 4-5
Wet: 4-5
EN ISO 105-X12:2002

Care

PERFORMANCE+
Easy to clean, longlasting fabrics

Washing conditions

Soiling and cleanability
4 FORD FLTM BN 112-08:2005


Dimensional change domestic washing and drying (%)
Warp: -1,6
Weft: -1,6
EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008

When confectioning or washing the sofa cover with velcro please attach a protective cloth.

Ignitability

BS5852 Source 0	Upon Request:
EN1021-Part 1:2006	BS5852 Source 1
CAL TB 117:2013	EN1021-Part 2:2006
NFPA 260:2013	BS 7176 Low Hazard
	UNI 9175 Clase 3IM

Environmental considerations



15% GRS recycled PET bottles
3% Circular yarn from own waste
80% Low impact yarn (PP)
2% CO

Life cycle analysis
Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint
3,72 kg CO_2 eq/m
11% less since 2020

Water consumption
66,86 liters/m
21,74% less since 2020

UNIVERSITAT POLITÈCNICA DE CATALUNYA
BARCELONATECH
Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology:
Life Cycle Analysis. ISO 14040 standard.

Functional unit:
1 linear meters, 140 cm width.

Database:
Own data, Ecoinvent 3.6 database and published data.

Calculation methodology:
Aware V1.02
ReCiPe Midpoint (H) 2016 v1.04
ReCiPe Endpoint (H) 2016 v1.04
IPCC 2013 GWP 100a v1.03
Software: SimaPro 9.4.0.1

Designed and Crafted in Terrassa (Barcelona)

Rev. nº: 7 - 24/08/2022 *Results that are underlined have been obtained by Crevin's internal laboratory and must therefore be seen as indicative.