

fire resistant

General Information



Composition

33%PP 30%PES 14%MA 12%CO REC
11%PES REC

Width

140 + 4cm

Weight

518 gr/m² ± 5 %
740 gr/lm ± 5 %

Custom code

UE: 5801.36.00
USA: 5801.36.00.20

Laboratory test number

IN-01418-2023-1

Specifications

Seam slippage resistance (mm)

Warp: 4,80
Weft: 1,80
EN ISO 13936/2:2004

Abrasion resistance (Fully worn off)

45.000 EN ISO 12947-2:2016

Abrasion resistance (change of aspect: 3000 cycles)

4 EN ISO 12947/4:1998
and EN 14465:2003 (Annex A)

Pilling resistance

Pilling 4-5
EN ISO 12945/2:2000

Lightfastness


≥6 EN ISO 105-B02:1998
and 105 B02/A01:2002

Colour fastness to rubbing

Wet: 4-5
Dry: 4-5
EN ISO 105-X12:2002

Care

Washing conditions



Soiling and cleanability

4 FORD FLTM BN 112-08:2005


Dimensional change domestic washing and drying (%)

Warp: -3
Weft: -3
EN ISO 3759:2008, EN ISO 6330:2000
and EN ISO 5077:2008

Ignitability

BS5852 Source 0	BS 7176 Low Hazard
EN1021-Part 1:2006	UNI 9175 Clase 3IM
CAL TB 117:2013	IMO Anexo 1 Parte 8
NFPA 260:2013	
BS5852 Source 1	
EN1021-Part 2:2006	

Environmental considerations



12% CO recycled
11% GRS recycled PET bottles
33% Low impact yarn (PP)
30% PES

Life cycle analysis

Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint

In process kg CO₂ eq / m

Water consumption

In process liters / m



UNIVERSITAT POLITÈCNICA DE CATALUNYA
BARCELONATECH

Escola Superior d'Enginyeries Industrial,
Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology:
Life Cycle Analysis. ISO 14040 standard.

Functional unit:
1 linear meters, 140 cm width.

Database:
Own data, Ecoinvent 3.6 database and published data.

Calculation methodology:
Aware V1.02
ReCiPe Midpoint (H) 2016 v1.04
ReCiPe Endpoint (H) 2016 v1.04
IPCC 2013 GWP 100a v1.03
Software: SimaPro 9.4.0.1



Designed and Crafted
in Terrassa (Barcelona)